

Specification		AM-JM-003	AM-JM-004
$Al_2O_3$ (%)		≥99.5	≥99.5
Surface Area ( $m^2/g$ )		≤12	≤12
D50 ( $\mu m$ )		15-20	1.5-2.5
Loose Density ( $cm^3/g$ )		0.5±0.1	0.5±0.1
Primary Crystal Size ( $\mu m$ )		3-5	0.5-1
Chemical Composition (ppm) ICP	Ca	≤2	≤2
	Na	≤300	≤300
	Fe	≤100	≤100
	Cu	≤2	≤2
	Mg	≤2	≤2
	Si	≤110	≤110
Cutting Effect		Strong/Super strong	Strong/Super strong
The Brightness of the light		Good	Good
Crystal Shapes		Spherical	Spherical
Appearance		White powder, no agglomeration, no foreign body.	
Distribution of Partial Size		It can be adjusted appropriately according to your needs.	